



FIBROX™ SPECIALTY FIBERS

FIBROX™ 300 MX – FIBROX™ 030 MX
• A QUALITY REINFORCEMENT/FILLER MATERIAL •

HIGH FIBER INDEX

EXCELLENT TENSILE STRENGTH

THERMAL STABILITY

CONSISTENT UNIFORMITY

NON ASBESTOS

FIBROX™ develops and supplies an engineered mineral fiber as a base ingredient for composite materials. Produced from high purity mineral ores in an electric arc furnace, the precisely designed fiber is used as a reinforcing material in a variety of composite end-uses including friction materials; vacuform shapes; plastics; paints; caulks and sealants.



Two versions of this world class engineered fiber are available: FIBROX™ 300 MX and FIBROX™ 030 MX with fiber indexes of 95% and 97% respectively. Additionally, application specific surface treatments can be integrated into the process.

FIBROX™ TECHNOLOGY, LP
TEL. 604-262-6782
WEB www.fibrox.com



FIBROX™ SPECIALTY FIBERS

FIBROX™ 300 MX – FIBROX™ 030 MX

TYPICAL PHYSICAL PROPERTIES

Color	Off White
Aspect Ratio	200-400
Density	2.7 - 2.9 GMS/CC
Hardness	6.0 Mohs
Fiber Diameter	5 - 6 Microns, by population
Fiber Diameter Range	1 - 20 Microns
Fiber Length (Average)	5-2 mm
Non-Fibrous Material	
300 MX	5 % average by weight
030 MX	3 % average by weight
Fiber Tensile Strength	80,000 psi
Fiber Tensile Modulus	1.5 - 6 x 10 ⁶ psi
Refractive Index	1.62-1.64
Shrinkage	2.4 % at 1600° F (871° C)
Devitrification Temperature	above 1550° F (843° C)
Melting Point	above 2000° F (1093° C)
Operating Temperatures	up to 1500° F (815° C)

TYPICAL CHEMICAL COMPOSITION

Silica	40 - 50%
Calcium	15 - 25%
Alumina	10 - 16%
Magnesia	5 - 10%
Other	6 - 10%

* Range for Major Oxides

STANDARD PACKAGING

50 lb. bags Note: Pulpable bags available.

TYPICAL END USES

Friction Materials	→	Reinforcement / Wear
Gaskets	→	Heat Resistance
Plastics	→	Shape Retention
Vacuform Shapes	→	High temp refractory ... Firelogs.
Caulks and Sealants	→	Heat resistance & viscosity modifier

All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.

SAFETY: Follow good safety and industrial hygiene practices during handling of all products. Take necessary precautions and wear the appropriate personal protective equipment as needed. Read material safety data sheets and related literature on products before specification and/or use.

For more information or to place an order, please call:

FIBROX CUSTOMER SERVICE
604-262-6782

Distributed by: